THIS ITEM SHALL CONSIST OF EXCAVATING TOPSOIL, PLACING GRANULAR MATERIAL AND APPLYING HERBICIDE, ON BOTH SIDES OF THE ROAD, AND IN ACCORDANCE WITH THE FOLLOWING:

ALL COLLECTED DEBRIS AND TOPSOIL, INCLUDING RHIZOMES, ROOTS, AND OTHER VEGETATIVE PLANT MATERIAL SHALL BE REMO/ED AND DISPOSED OF AS SPECIFIED IN SECTION 203.05 OF THE CONSTRUCTION AND MATERIAL SPECIFICATIONS.

ANY REMOVAL OF THE ABOVE ITEMS WHICH EXTEND BELOW THE PROPOSED SUBGRADE SHALL BE REPLACED WITH COMPACTABLE GRANULAR MATERIAL CONFORMING TO 203.02 AND SHALL BE PLACED TO GRADE AS DETAILED ON THE TYPICAL SECTION OR AS APPROVED BY THE ENGINEER.

HERBICIDE SHALL BE TREFLAN E.C., SPIKE, OR AN APPROVED EQUAL AND SHALL BE APPLIED TO THE PREPARED AREA AFTER FINAL LEVELING AND GRADING HAS BEEN COMPLETED. THE APPLICATION SHALL BE JUST PRIOR TO PAVING AND SHALL STRICTLY ADHERE TO THE MANUFACTURER'S LABLEL INSTRUCTIONS,

ONLY PROPERLY LICENCED PERSONNEL SHALL APPLY HERBICIDES AS REQUIRED BY THE OHIO REVISED CODE.

ALL EQUIPMENT, MATERIALS, AND LABOR REQUIRED TO PERFORM THE WORK OUTLINED ABOVE SHALL BE INCLUDED FOR PAYMENT UNDER ITEM 203 - LINEAR GRADING.

THE FOLLOWING QUANTITY HAS BEEN CARRIED TO THE GENERAL SUMMARY: ITEM 203 - LINEAR GRADING 147 STA.

ITEM 251 - PARTIAL DEPTH PAVEMENT REPAIR:

AN ESTIMATED QUANTITY HAS BEEN PROVIDED AND SHALL BE USED AS DIRECTED BY THE ENGINEER TO REPAIR THE ROADWAY PAVEMENT AND PAVED SHOULDERS.

DEPTH OF REMOVAL SHALL TYPICALLY BE 3 IN. UNLESS OTHERWISE DIRECTED BY THE ENGINEER.

THE INTENT OF THIS ITEM OF WORK IS TO REPAIR ONLY THE AREAS THAT CANNOT BE CORRECTED BY THE PLANING PROCESS. THIS WOULD INCLUDE SEVERE OR DEEP POTHOLES, LOW AREAS AND AREAS WITH LOOSE OR MISSING ASPHALT. AREAS WHICH HAVE EXTENSIVE CRACKING BUT ARE STRUCTURALLY SOUND SHALL NOT USE THIS ITEM.

THE FOLLOWING CONTIGENCY QUANTITY HAS BEEN CARRIED TO THE GENERAL SUMMARY

ITEM 251 - PARTIAL DEPTH PAVEMENT REPAIR 1800 SQ.YD.

ITEM 621 - RAISED PAVEMENT MARKER

RAISED PAVEMENT MARKERS SHALL BE INSTALLED IN ACCORDANCE WITH STANDARD DRAWINGS TC-65.10, TC-65.11 AND TC-65.12.

ITEM 407 - TACK COAT ITEM 407 - TACK COAT FOR INTERMEDIATE COURSE

THE RATE OF APPLICATION OF THE 407 - TACK COAT SHALL BE SUBJECT TO ADJUSTMENTS. AS DIRECTED BY THE ENGINEER. PLAN QUANTITIES INDICATE AN AVERAGE APPLICATION RATE OF 0.10 GAL/SQ.YD. FOR ESTIMATION PURPOSES ONLY.

THE RATE OF THE 407 TACK COAT FOR INTERMEDIATE COURSE SHALL BE SUBJECT TO ADJUSTMENT AS DIRECTED BY THE ENGINEER. PLAN QUANTITIES INDICATE AN AVERAGE APPLICATION RATE OF 0.05 GAL/SQ.YD. FOR ESTIMATION PURPOSES ONLY.