

RE: Parcel 9 - 36628 Vine Street, East Lake, OH

PEC LAB #	CLIENT ID #	LOCATION	COLOR
08WB-07103	LAK2PCL9#5	1st Fir Front Office Wall	Bge/Tan/Crm
Texture/Description:	Solid/Plasterboard	Chrysotile: 0%	Tremolite: 0% Anthophyllite: 0%
TOTAL ASBESTOS:	0 %	Amosite: 0%	Actinolite: 0% Crocidolite: 0%
Cellulose: 14%	Fiber Glass: 0%	Others: 0%	Filler/Binder: 86 %

PEC LAB #	CLIENT ID #	LOCATION	COLOR
08WB-07104	LAK2PCL9#6	1st Fir Front Office Ceiling	Bge/Tan/Wht
Texture/Description:	Solid/Plasterboard	Chrysotile: 3%	Tremolite: 0% Anthophyllite: 0%
TOTAL ASBESTOS:	3 %	Amosite: 0%	Actinolite: 0% Crocidolite: 0%
Cellulose: 18%	Fiber Glass: 0%	Others: 0%	Filler/Binder: 79 %

PEC LAB #	CLIENT ID #	LOCATION	COLOR
08WB-07105	LAK2PCL9#7	1st Fir Rear Office Wall	Bge/Tan/Crm
Texture/Description:	Solid/Plasterboard	Chrysotile: 2%	Tremolite: 0% Anthophyllite: 0%
TOTAL ASBESTOS:	2 %	Amosite: 0%	Actinolite: 0% Crocidolite: 0%
Cellulose: 14%	Fiber Glass: 0%	Others: 0%	Filler/Binder: 84 %

PEC LAB #	CLIENT ID #	LOCATION	COLOR
08WB-07106a	LAK2PCL9#8	1st Fir Front Office Floors	White
Texture/Description:	Solid/Vinyl Tile	Chrysotile: 0%	Tremolite: 0% Anthophyllite: 0%
TOTAL ASBESTOS:	0 %	Amosite: 0%	Actinolite: 0% Crocidolite: 0%
Cellulose: 0%	Fiber Glass: 0%	Others: 0%	Filler/Binder: 100%

PEC LAB #	CLIENT ID #	LOCATION	COLOR
08WB-07106b	LAK2PCL9#8	1st Fir Front Office Floors	Yellow
Texture/Description:	Solid/Mastic	Chrysotile: 0%	Tremolite: 0% Anthophyllite: 0%
TOTAL ASBESTOS:	0 %	Amosite: 0%	Actinolite: 0% Crocidolite: 0%
Cellulose: 0%	Fiber Glass: 0%	Others: 3%	Filler/Binder: 97 %

PEC LAB #	CLIENT ID #	LOCATION	COLOR
08WB-07107a	LAK2PCL9#9	2nd Fir Stairway Wall End Joint	Grey
Texture/Description:	Solid/Plaster	Chrysotile: 3%	Tremolite: 0% Anthophyllite: 0%
TOTAL ASBESTOS:	3 %	Amosite: 0%	Actinolite: 0% Crocidolite: 0%
Cellulose: 2%	Fiber Glass: 0%	Others: 4%	Filler/Binder: 91 %

PEC LAB #	CLIENT ID #	LOCATION	COLOR
08WB-07107b	LAK2PCL9#9	2nd Fir Stairway Wall End Joint	White
Texture/Description:	Solid/Top Coat	Chrysotile: 0%	Tremolite: 0% Anthophyllite: 0%
TOTAL ASBESTOS:	0 %	Amosite: 0%	Actinolite: 0% Crocidolite: 0%
Cellulose: 0%	Fiber Glass: 0%	Others: 0%	Filler/Binder: 100%