DESCRIPTION:
THIS ITEM OF WORK SHALL CONSIST OF FACING SIDEWALK
STYLE PARAPETS, USING CAST IN PLACE CONCRETE,
TO OBTAIN THE SINGLE SLOPE BARRIER SHAPE AS
SHOWN IN THE PLANS. REMOVAL: THE CONTRACTOR SHALL
CAREFULLY REMOVE THE EXISTING FENCE, CURB PLATES,
EXISTING CONCRETE WALK AND ANY SOUND CONCRETE
NECESSARY TO OBTAIN A MINIMUM 4 INCH THICKNESS OF
NEW CONCRETE. ALL LOOSE OR UNSOUND CONCRETE
SHALL ALSO BE REMOVED.

SLIP FORMING SHALL NOT BE PERMITTED.

DOWEL HOLES AND REINFORCING STEEL:

DOWEL HOLES SHALL BE AS PER ITEM 510 USING EPOXY
GROUT AS PER 705.20. SE501 BARS SHALL BE 4" FROM
DEFLECTION JOINTS. SE502 BARS SHALL BE 6" FROM
DEFLECTION JOINTS.

EXISTING REINFORCING STEEL BARS IN THE AREA OF
THE DOWEL HOLE SHALL BE LOCATED WITH THE AID OF
A REINFORCING STEEL BAR LOCATOR
PRIOR TO DRILLING THE HOLES. IF AN EXISTING BAR IS
ENCOUNTERED AT THE SAME LOCATION AS A PROPOSED
DOWEL HOLE, THE DOWEL HOLE SHALL BE MOVED
TO EITHER SIDE OF THE EXISTING BAR. ALL
REINFORCING STEEL, DOWEL HOLES AND GROUTING
SHALL BE INCLUDED WITH ITEM 517 FOR PAYMENT.

SURFACE PREPARATION:
THE PARAPET SURFACE IN CONTACT WITH THE
REFACING SHALL BE THOROUGHLY CLEANED BY
ABRASIVE BLASTING, WITH ENVIRONMENTAL
CONTROLS, FOLLOWED BY AN AIR BLAST. USE OF
HAND TOOLS MAY BE NECESSARY TO REMOVE SCALE
FROM ANY EXPOSED REINFORCING STEEL. THE SURFACE
SHALL BE MADE FREE FROM SPALLS, LATENCE, AND ALL
TRACES OF FOREIGN MATERIAL. DETERGENT CLEANING
SHALL PRECEDE BLAST CLEANING AS NECESSARY TO
ENSURE REMOVAL OF CONTAMINANTS THAT ARE
DETRIMENTAL TO ACHIEVING AN ADEQUATE BOND.

I'/2" DEEP AND '/4" WIDE DEFLECTION JOINTS AT ALL EXISTING DEFLECTION JOINT LOCATIONS AS WELL AS MIDWAY BETWEEN SHICH JOINTS SHALL BE SAWED IN THE NEW CONCRETE. THE JOINTS SHALL BE SAWED AS SOON AS POSSIBLE AFTER PLACEMENT, BEFORE ANY SHRINKAGE CRACKS DEVELOP. ALL JOINTS SHALL BE SAWED WITHIN 24 HOURS. THE USE OF AN EDGE GUIDE, FENCE OR JIG IS REQUIRED TO ENSURE THAT THE JOINT IS STRAIGHT, TRUE AND ALIGNED ON ALL FACES OF THE PARAPET. THE PERIMETER OF THE DEFLECTION JOINT SHALL BE SEALED A MINIMUM I'/2" DEEP USING A CAULKING MATERIAL CONFORMING TO FEDERAL SPECIFICATION TT-S-00227E.

CURING SHALL BE AS PER 511.14 METHOD(b). IF THE CONTRACTOR USES CHEMASTERS EPOXY-URETHANE SYSTEM FOR "SEALING OF CONCRETE SURFACES" HE MAY USE THE EPOXY PORTION OF THAT SYSTEM (CHEMASTERS "SAFE-CURE & SEAL EPX") AS THE CURING COMPOUND TO MEET THE REQUIREMENTS OF 511.14(b). IF USED, REMOVAL OF THE CURING COMPOUND SHALL NOT BE REQUIRED PRIOR TO APPLYING THE URETHANE TOP COAT.

MINIMUM CONCRETE COVER SHALL BE 2" .

MATERIALS: REINFORCING STEEL - 709.00, GRADE 60

CONCRETE:
CONCRETE SHALL BE AS PER SUPPLEMENTAL
SPECIFICATION 844, AS PER PLAN,
THE MINIMUM CONCRETE SLUMP DURING
PLACEMENTOF ALL CONCRETE PARAPETS SHALL BE
6 INCHES.

CONCRETE TABLE: QUANTITIES PER CUBIC YARD AGGREGATES (SSD)

MIX 4, AS PER PLAN (GGBF SLAG + MICROSILICA)

FINE AGGREGATE (LB)	GRAVEL	LIMESTONE	SLAG
	1245	1245	1246
#8 COARSE AGGREGATE (LB) #57 COARSE	360	360	315
AGGREGATE (LB) TOTAL (LB)	1315	1335	1155
	2920	2940	2716
CEMENT CONTENT (LB) GGBF SLAG (LB)	400 170	400	400 170
MICROSILICA (LB) WATER TO CEMENTITIO	30	30	30
RATIO MAX.	0.42	0.42	0.42
AIR CONTENT, +/-2%	7%	7%	7%

THE WEIGHTS SPECIFIED IN THE CONCRETE TABLE WERE CALCULATED FOR MATERIALS OF THE FOLLOWING BULK SPECIFIC GRAVITIES (SSD): NATURAL SAND AND GRAVEL 2.62, LIMESTONE SAND 2.68, LIMESTONE 2.65, SLAG 2.30, FLY ASH 2.65, GGBF SLAG 2.90, MICROSILICA SOLID 2.20, AND PORTLAND CEMENT 3.15. FOR AGGREGATES OF SPECIFIC GRAVITIES DIFFERING MORE THAN PLUS OR MINUS 0.02 FROM THESE, THE WEIGHTS IN THE TABLE WILL BE CORRECTED.

METHOD OF MEASUREMENT:
THE QUANTITY SHALL BE THE ACTUAL LENGTH OF
RAILING FACED AS MEASURED FROM EXPANSION JOINT
TO EXPANSION JOINT. THIS ITEM SHALL INCLUDE THE
FURNISHING OF ALL LABOR, EQUIPMENT AND MATERIALS
NECESSARY TO COMPLETE THIS WORK. ALL COSTS OF
REMOVAL, DOWEL HOLES, REINFORCING STEEL, CONCRETE
AND SHRINKAGE CONTROL JOINTS, COMPLETE AND IN
PLACE, SHALL BE INCLUDED IN THE UNIT PRICE BID
FOR:

EM UNIT DESCRIPTION 7 FEET RAILING FACED, AS PER PLAN

ITEM 844 HIGH PERFORMANCE CONCRETE, MISC; DECK AND APPROACH SLAB EXTENSION, AS PER PLAN

THE PROVISIONS OF 844 SHALL APPLY EXCEPT AS NOTED BELOW.

THE MINIMUM CONCRETE SLUMP DURING PLACEMENT OF ALL CONCRETE PARAPETS SHALL BE 6 INCHES. THE MAXIMUM SLUMP ALLOWED DURING PLACEMENT IS 8 INCHES.

FORMS SHALL NOT BE REMOVED UNTIL AT LEAST 2 HOURS AFTER THE FINAL SET. DETERMINATION OF THE FINAL SET SHALL BE AS PER ASTM C266 (GILLMORE NEEDLE). TESTING SHALL BE PERFORMED BY THE CONTRACTOR AT NO COST TO THE STATE.

FENCE POST ANCHORS: ANCHOR BOLTS FOR FENCE POSTS SHALL BE CAST IN PLACE.

DRILLING AND GROUTING HOLES:
DOWEL HOLES SHALL BE PER CMS 510. USE NON-SHRINK
EPOXY GROUT PER 705.20. PAYMENT SHALL BE
INCLUDED WITH THE APPROPRIATE ITEM 844.

MIX OPTIONS: ALL CONCRETE SHALL BE MIX 4, AS PER PLAN. THE FOLLOWING PROPORTIONS WILL BE USED AS A STARTING MIX DESIGN.

CONCRETE TABLE: QUANTITIES PER CUBIC YARD AGGREGATES (SSD)

MIX 4, AS PER PLAN (GGBF SLAG + MICROSILICA)

FINE AGGREGATE (LB)	GRAVEL	LIMESTONE	SL AG
	1245	1245	1246
#8 COARSE AGGREGATE (LB) #57 COARSE	360	360	315
AGGREGATE (LB) TOTAL (LB) CEMENT CONTENT (LB)	1315	1335	1155
	2920	2940	2716
	400	400	400
GGBF SLAG (LB)	170	170	170
MICROSILICA (LB)	30	30	30
WATER TO CEMENTITIOU RATIO MAX. AIR CONTENT, +/-2%	S 0.42 7%	0.42 7%	0.42 7%

THE WEIGHTS SPECIFIED IN THE CONCRETE TABLE WERE CALCULATED FOR MATERIALS OF THE FOLLOWING BULK SPECIFIC GRAVITIES (SSD): NATURAL SAND AND GRAVEL 2.62, LIMESTONE SAND 2.68, LIMESTONE 2.65, SLAG 2.30, FLY ASH 2.65, GGBF SLAG 2.90, MICROSILICA SOLID 2.20, AND PORTLAND CEMENT 3.15. FOR AGGREGATES OF SPECIFIC GRAVITIES DIFFERING MORE THAN PLUS OR MINUS 0.02 FROM THESE, THE WEIGHTS IN THE TABLE WILL BE CORRECTED.

DECK TEXTURING: THE DECK SURFACE SHALL BE RAKED TO PROVIDE A ROUGH MACRO BOND SURFACE FOR THE MSMC OVERLAY.

BASIS OF PAYMENT: PAYMENT FOR THE ABOVE COMPLETED AND ACCEPTED QUANTITIES WILL BE MADE AT THE CONTRACT BID PRICE FOR:

ITEM UNITS DESCRIPTION
844E49500 CUBIC YARD HIGH PERFORMANCE CONCRETE
MISC; DECK AND APPROACH
SLAB EXTENSION, AS PER PLAN

REPLACEMENT OF EXISTING REINFORCING STEEL

ANY EXISTING REINFORCING STEEL BARS WHICH ARE TO BE INCORPORATED INTO THE NEW WORK AND ARE MADE UNUSABLE BY CONCRETE REMOVAL OR OTHER CONTRACTOR OPERATIONS SHALL BE REPLACED WITH NEW EPOXY COATED REINFORCING STEEL OF THE SAME SIZE AT THE CONTRACTOR'S COST PER CMS 509.

<u> [TEM 842 - CONCRETE MISC.: REPLACEMENT OF EXISTING REINFORCING STEEL</u>

ANY EXISTING REINFORCING BARS DEEMED BY THE ENGINEER TO BE UNUSABLE BECAUSE OF CORROSION SHALL BE REPLACED WITH NEW EPOXY COATED REINFORCING STEEL PER CMS 509.

THE NUMBER OF POUNDS OF REINFORCING STEEL PAID FOR SHALL BE THE ACTUAL POUNDS OF REPLACEMENT REINFORCING STEEL FURNISHED AND INSTALLED BY THE CONTRACTOR AS DIRECTED BY THE ENGINEER TO REPLACE CORROSION DAMAGED REINFORCING STEEL.

PAYMENT FOR ALL THE ABOVE DESCRIBED LABOR AND MATERIALS WILL BE MADE AT THE CONTRACT PRICE BID PER POUND FOR ITEM 842 - CONCRETE, MISC.: REPLACEMENT OF EXISTING REINFORCING STEEL.

<u>ITEM 842 - CONCRETE MISC.: DRILLING AND GROUTING</u> <u>DOWEL HOLES</u>

THIS CONTINGENCY QUANTITY SHALL INCLUDE THE DRILLING OF HOLES PER CMS 510 INTO CONCRETE OR MASONRY AND THE FURNISHING AND PLACEMENT OF GROUT INTO HOLES AS DIRECTED BY THE ENGINEER. NONSHRINKING EPOXY GROUT SHALL BE USED PER CMS 705.20.

PAYMENT FOR ALL THE ABOVE DESCRIBED LABOR AND MATERIALS WILL BE MADE AT THE CONTRACT PRICE BID FOR ITEM 842 - CONCRETE MISC.: DRILLING AND GROUTING DOWEL HOLES.

SCUPPER DEPRESSIONS

THE EXISTING SCUPPERS MUST REMAIN IN SERVICE
IN ORDER TO DRAIN THE BRIDGE. THE DEPRESSIONS
IN THE CONCRETE OVERLAY SURROUNDING THE
SCUPPERS ON THE NORTH SIDE OF THE BRIDGE
MUST BE ELIMINATED PRIOR TO OPENING THE
WIDENING TO TRAFFIC. CONCRETE WITHIN THE
DEPRESSION SHALL BE REMOVED DOWN TO THE TOP OF
THE SCUPPER AND REPLACED UP TO THE NORMAL WEARING
SURFACE TOP WITH MICROSILICA MODIFIED CONCRETE,
AS DIRECTED BY THE ENGINEER. ONLY THE FULL
SURFACE AREA OF THE SCUPPER SHALL REMAIN
UNFILLED. PAYMENT FOR FILLING SCUPPER
DEPRESSIONS SHALL BE INCLUDED IN ITEM 847 MICROSILICA MODIFIED CONCRETE OVERLAY (VARIABLE
THICKNESS).

ITEM 847 - MICROSILICA MODIFIED CONCRETE OVERLAY

(1¾") THICKNESS)

PROPER HAND FINISHING EQUIPMENT MAY BE USED TO PLACE THE OVERLAY AS DIRECTED BY THE ENGINEER. THE CONTRACTOR MUST DEMONSTRATE TO THE SATISFACTION OF THE ENGINEER PRIOR TO PLACEMENT THAT THE HAND METHODS WILL ACHIEVE SATISFACTORY CONSOLIDATION AND SCREEDING OF THE OVERLAY.

STATE ROUTE 44

DESIGNED DRAWN

MKB

MKB

CHECKED REVISED

P

0

~

W

TUR

Œ

S

UC. BRI

LAKE COUNTY 4K-2/44-13.05/4.

3/