

885.05 Quality Control Quality control will consist of the following items:

A. Contractor Quality Control Specialist. Before any work begins, the Contractor shall designate one individual on each project as a Quality Control Specialist (only one person per project will be necessary unless the Contractor is working at more than 3 sites simultaneously). In which case, it will be necessary to provide an additional Quality Control Specialist for each additional three (or portion of three) sites being painted simultaneously. This person will not be a Foreman or member of the Contractor's production staff (ie. he will not abrasive blast, paint, recover spent abrasives, etc.). He will not be involved in any other miscellaneous tasks (ie. mixing paint, running errands, running or working on equipment, etc.) while any production work is taking place. Documentation that personnel performing quality control related functions are qualified shall be submitted to the Engineer prior to allowing the Quality Control Specialist (QCS) to begin work. Documentation/verification shall be provided to the Engineer that the QCS has received formal training from one of the following: KTA Tator, S. G. Pinney, or Corrosion Control Consultants. He shall be equipped with material safety data sheets, product data sheets, tools and equipment to provide quality control on all facets of the work and shall have a thorough understanding of the plans and specifications pertaining to this project. He shall be responsible for inspecting the equipment at the specified intervals, the abrasives, and the work, at all quality control points. He shall also be responsible for verifying that all work is done within the specified work limitations. He shall cooperate with the Inspector and compare and document quality control readings. He shall have the authority to stop work and the responsibility to inform the Contractor's Foreman of nonconforming work.

B. Quality Control Points. Quality control points (QCP) are points in time when one phase of the work is complete and ready for inspection by both the Contractor and the Engineer prior to continuing with the next operational step. At these points: The Contractor shall afford access to inspect all affected surfaces. If inspection indicates a deficiency, that phase of the work shall be corrected in accordance with these specifications prior to beginning the next phase of work. Discovery of defective work or material after a Quality Control Point is past or failure of the final product before final acceptance, shall not in any way prevent rejection or obligate the State of Ohio to final acceptance.

Quality Control Points (QCP)	PURPOSE
1. Solvent Cleaning	Remove asphaltic cement, oil, grease, salt, dirt, etc. followed by washdown
2. Grinding Flange Edges	Remove sharp corners,
3. Containment/Waste Disposal	Contain, collect & dispose of abrasive blasting debris
4. Abrasive Blasting	Blasted surface to receive paint
5. Prime Coat Application	Check surface cleanliness; apply prime coat; check coating thickness
6. Removing Fins, Tears, slivers	Remove surface defects and slivers
7. Caulking	Caulk areas
8. Intermediate Coat Application	Check surface cleanliness; apply intermediate coat, check coating thickness
9. Finish Coat Application	Check surface cleanliness, apply finish coat, check coating thickness
10. Final Review	Visual inspection of system for Acceptance and check total system thickness.

885.06 Surface Preparation. This item shall also consist of solvent cleaning, grinding flange edges, abrasive blasting, and providing a wash facility for the Engineer and Inspectors.

A. Solvent Cleaning (QCP #1). All traces of asphaltic cement, oil, grease, diesel fuel deposits, and other soluble contaminants, shall be removed by solvent cleaning (QCP #1) (see SSPC-SP 1 Solvent Cleaning for recommended practices). Under no circumstances shall any abrasive blasting be done to areas with asphaltic cement, oil, grease, or diesel fuel deposits. All solvent cleaned areas shall be subsequently washed before abrasive blasting as detailed below.

Washing shall be accomplished with potable water having a nozzle pressure of at least 1,000 PSI (7 Mpa) and a delivery rate of not less than 4 gallon (15 L) per minute. The Contractor, shall provide equipment specifications to verify the above. The equipment shall also be equipped with gauges to verify the pressure. The nozzle shall be held at a maximum of 12 inches (300 mm) from the surface being washed.

B. Grinding Flange Edges (QCP #2). All exposed bottom flange edges of longitudinal rolled and welded beams shall be rounded to a radius of 1/8 inch plus or minus 1/16 inch (3 mm plus or minus 1.5 mm) before abrasive blasting. This work may be done without weather and temperature restrictions. This work is included with surface preparation for payment.

C. Containment/Waste Disposal (QCP #3). Waste material generated by abrasive blasting operations is a solid waste and shall be handled as follows:
(1) Contained, (2) Collected, (3) Stored, (4) Evaluated, (5) Properly disposed.